This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6:
H01L 21/3065
A1
(11) International Publication Number: WO 99/49506
(43) International Publication Date: 30 September 1999 (30.09.99)

(21) International Application Number: PCT/GB99/00774

(22) International Filing Date: 16 March 1999 (16.03.99)

(30) Priority Data:
9805927.2
9904925.6
20 March 1998 (20.03.98)
GB
9904925.6
4 March 1999 (04.03.99)
GB

(71) Applicant (for all designated States except US): SURFACE TECHNOLOGY SYSTEMS LIMITED [GB/GB]; Imperial Park, Newport, Gwent NP1 9UJ (GB).

(72) Inventor; and


(75) Inventor/Applicant (for US only): MCQUARRIE, Andrew, Duncan [GB/US]; 16066 Highland Drive, San Jose, CA 95127 (US).

(74) Agents: EASTWOOD, Simon, Christopher et al.; Wynne-Jones, Laine & James, 22 Rodney Road, Cheltenham, Gloucestershire GL50 1JJ (GB). (81) Designated States: JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

(54) Title: METHOD AND APPARATUS FOR MANUFACTURING A MICROMECHANICAL DEVICE



(57) Abstract

There is disclosed a method of manufacturing a micromechanical device. The method comprises the steps of: (a) etching a substrate (1), having a mask (2) thereon, through an opening in the mask to a desired depth to form a trench (6) having a side wall (4) and a base (5) in the substrate (1); (b) depositing a layer of a protecting substance (7) on the exposed surfaces of the substrate and mask; (c) selectively removing the protecting substance (7) from the base (5); and (d) etching the base (5) using a fluorine—containing etchant. Also disclosed is a micromechanical device formed by the method and an apparatus for manufacturing the micromechanical device.

K. 1

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

I	AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
١	AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
I	AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
ı	AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
١	AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
ı	BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
ı	BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
ı	BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
ı	BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
Į	BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
ı	BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
ı	BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
ı	BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
ı	CA	Canada	IT	Italy	MX	Mexico	uz	Uzbekistan
ı	CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
1	CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
1	СН	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
١	CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
١	CM	Cameroon		Republic of Korea	PL	Poland		
I	CN	China	KR	Republic of Korea	PT	Portugal		
١	CU	Cuba	KZ	Kazakstan	RO	Romania		
	CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
l	DE	Germany	LI	Liechtenstein	SD	Sudan		
	DK	Denmark	LK	Sri Lanka	SE	Sweden		
ı	EE	Estonia	LR	Liberia	SG	Singapore		

1

Method and Apparatus for Manufacturing a Micromechanical Device

The present invention relates to a method and apparatus for manufacturing a micromechanical device using a fluorine etchant source, for example xenon difluoride (XeF_2). Xenon difluoride is a dry isotropic gas phase etchant, which provides a gentle etch for silicon at low temperature. Xenon difluoride is usually supplied in the form of colourless crystals which sublime without decomposition. The sublimation pressure for XeF_2 is approximately 4 Torr.

5

10

15

20

25

A current method of manufacturing a micromechanical device uses the steps of anisotropic etching, mask removal, silicon oxide deposition, selective oxide etching, and isotropic etching of silicon with a SF₆ plasma and oxide strip. However, this method requires many steps which results in long cycle times and a high cost. Other methods etch down to a buried oxide layer of silicon dioxide and selectively stop the anisotropic silicon etch at that interface. The silicon oxide is then selectively removed by HF to release the silicon structures. However, this method requires the use of wafers having a buried oxide layer which are very costly as well as additional equipment for HF based etching. Furthermore, liquid HF etching itself has considerable potential for stiction issues.

According to a first aspect of the present invention, there is provided a method of manufacturing a micromechanical device comprising the steps of:

(a)c .

15

2

- (a) etching a substrate, having a mask thereon, through an opening in the mask to a desired depth to form a trench having a side wall and a base in the substrate;
- (b) depositing a layer of a protecting substance on the exposed surfaces of the substrate and mask;
 - (c) selectively removing the protecting substance from the base; and
 - (d) etching the base using a fluorine-containing etchant.

The fluorine-containing etchant may be a gas or vapour used to etch the substrate in the absence of a plasma.

Preferably, the fluorine-containing etchant is XeF₂. However, other vapours such as F₂ or ClF₃ (which will either etch or enhance the etch rate of silicon in the gas phase) as discussed in our co-pending British Patent Application No. 9904925.6 may be equally applied either as a replacement to XeF₂, or in the form of a mixture, for example with XeF₂. Thus, whilst the use of XeF₂ is discussed below in detail, other gases could be used.

Conveniently, the mask may be provided with a plurality of openings therein.

The method may further comprise the step of removing the mask and remaining protecting substance. This removal may be by means of a plasma. The substrate is preferably formed of silicon.

In a preferred embodiment, the mask is deposited by a photolithographic process.

The substrate is preferably etched by substantially anisotropic etching. The anisotropic etching may conveni-

24 6 20

5

10

15

20

25

3

ently be performed using the methods described in EP-A-0822582 and EP-A-0822584, the contents of which are incorporated herein by reference.

The use of XeF₂ in a method and apparatus for etching a workpiece are disclosed in British Patent Application No. 9709659.8, the contents of which are incorporated herein by reference.

The protecting substance may be of the form C_YF_X (where X and Y may be any suitable value) such as CF_X polymeric chains, where x may be 2. Thus, the protecting substance may be of the general formula $n(CF_2)$. One example may be cross-linked PTFE. The deposition may be performed by generating a plasma, for example an RF plasma, with an appropriate source gas, for example C_4F_8 . In a preferred embodiment, a typical deposition thickness of the protecting substance is in the range of about 10 to 100 nm. Alternatively, the protecting substance may be of the form C_YH_X such as CH_X polymeric chains, where x may be 2. Thus, it may be of the general formula $n(CH_2)$. In this case the source gas may be CH_4 , for example. Again X and Y may be any suitable value.

The protecting substance may be selectively removed from any or all of the surfaces other than the side wall and etching with the fluorine-containing etchant may take place on all resulting unprotected areas.

The protecting substance may selectively be removed by a plasma such as oxygen or (well known) mixtures with argon, helium, or nitrogen for example. The requirement for selec5

10

15

25

tive removal may be achieved by a suitable plasma process as known in the art.

The etching with the fluorine-containing etchant may be isotropic etching of the unprotected areas of the substrate.

According to a second aspect of the present invention, there is provided a device formed by the above method.

The device may be formed as a series of adjacent fingers separated by trenches. A fluorine-containing etchant, for example XeF₂, may be used to undercut such that the trenches are in communication.

According to a third aspect of the present invention, there is provided an apparatus for manufacturing a micromechanical device comprising:

- (a) means for etching a substrate, having a mask thereon, to a desired depth;
 - (b) means for depositing a layer of a protecting substance on the exposed surfaces of the substrate and mask;
 - (c) means for selectively removing the protecting substance; and
- 20 (d) means for providing a fluorine-containing etchant for etching the unprotected areas.

The means for depositing the protecting substance may be means for generating a plasma. The means for selectively removing the protecting substance preferably includes means for providing a suitable plasma.

In a preferred embodiment, the apparatus may further comprise means for removing the mask and the remaining protecting substance and this means may be a plasma source,

5

20

car, com

preferably an oxygen plasma source.

Although the invention has been described above, it is to be understood that it includes any inventive combination of the features set out above or in the following description.

The invention may be performed in various ways and a specific embodiment will now be described, by way of example, with reference to the accompanying drawings in which:

10 Figure 1 is a cross section of a silicon substrate having a pattern photoresist;

Figure 2 is a cross section view corresponding to that in Figure 1 in which the silicon has been etched;

Figure 3 shows a cross sectional view corresponding to

15 Figures 1 and 2 in which a protecting layer has been deposited;

Figure 4 shows a corresponding cross sectional view in which the protecting layer has been selectively removed;

Figure 5 shows a corresponding cross section view showing a partial etch of the substrate;

Figure 6 shows a corresponding cross section view in which etching has been completed;

Figure 7 is a top view of inter-digitated silicon fingers formed by the method of the present invention;

25 Figure 8 is a cross sectional view of Figure 7 along the line A-A; and

Figure 9 shows a schematic view of an apparatus of the present invention.

6

Figure 1 shows a silicon substrate 1 on which is a patterned photoresist (mask) 2. The silicon substrate 1 is patterned by the use of photolithographic processes. Between the parts of the photoresist 2 are channels 3.

5

10

15

20

25

As shown in Figure 2, the silicon is then etched to a desired depth by anisotropic etching in a downward direction so that there is as little etching of the side walls of the formation as possible. The etching may be carried out by any suitable process. In this respect reference is made to EP-A-0822582 and EP-A-0822584. The etching leads to formation of side walls 4 and bases 5. The series of side walls 4 and bases 5 together form trenches 6.

As shown in Figure 3, a layer of a protecting substance is deposited on the exposed surfaces to a thickness of about 100 nm. The deposited layer is shown at 7. This layer is deposited in the process chamber by generating a RF plasma with the source gas being C_4F_8 and provides a layer of C_7F_8 as mentioned above. One example is thought to be a layer of cross-linked PTFE.

Turning to Figure 4, an argon/oxygen mixture selectively removes the C_yF_x (for example the cross-linked PTFE) from the horizontal surfaces shown by upper surfaces 8 and bases 5. The requirement may be achieved by using, for example, low pressure reactive ion etching or inductively coupled plasma technique as mentioned above.

It is then possible to etch the unprotected silicon areas on the bases 5. Figure 5 shows the result of a partial etch which leads to etches 9. In the present

7

invention, XeF₂ is used to isotropically etch the unprotected silicon areas leading to the etches 9.

Figure 6 shows the result of etching to completion by XeF_2 followed by an oxygen plasma to remove both the photoresist 2 and remaining deposited layer 7. This etching provides the completed etch indicated by 10.

5

10

15

20

25

The method described above provides a simple approach to releasing silicon microstructures after they have been formed by anisotropic etching. Thus, Figure 5, as described above shows a structure in which the release process is happening and Figure 6 shows a structure when released. The method may be carried out sequentially in the same process chamber as the anisotropic etch. Thus, all the steps may be carried out in the same process chamber.

In the sequence shown by Figures 1 to 6, an example structure of inter-digitated silicon fingers is produced. The method may be applied to either bulk or polysilicon based structures.

Figures 7 and 8 show the final form of the resulting silicon microstructure in which inter-digitated silicon fingers 10 are shown.

Whilst the microstructures resulting from the present invention have a number of applications, typical applications for such structures may be accelerometers and gyroscopes which are based upon capacitance sensing between the silicon fingers by means of anchoring one set of silicon fingers 10 and allowing the other set to move when force is applied, this movement being sensed by the change in

8

capacitance.

5

10

15

λ , (, 🖢

Figure 9 illustrates a reactor chamber 11 suitable for use in the present invention. Typically, a vacuum chamber 12 incorporates a support electrode 13 for receiving a substrate 14 and a further spaced electrode 15. The substrate 14 may be pressed against the support 13 by a clamp 16. The chamber 12 is surrounded by a coil 17 and fed by a RF source which is used to induce a plasma in the chamber 12 between electrodes 13 and 15. Alternatively a microwave power supply may be used to create the plasma. In both cases there is a need to create a plasma bias, which can be either RF or DC and can be connected to the support electrode 13 so as to influence the passage of ions from the plasma onto substrate 14. An example of such an adjustable bias means is indicated at 19. The chamber is provided with a gas inlet port 20 and an exhaust port 21.

\$ 11 Jan

25

9

Claims

- 1. A method of manufacturing a micromechanical device comprising the steps of:
- (a) etching a substrate, having a mask thereon, through anopening in the mask to a desired depth to form a trench having a side wall and a base in the substrate;
 - (b) depositing a layer of a protecting substance on the exposed surfaces of the substrate and mask;
- (c) selectively removing the protecting substance from the base; and
 - (d) etching the base using a fluorine-containing etchant.
 - 2. A method according to claim 1, wherein the fluorine-containing etchant is a gas or vapour used to etch the substrate in the absence of a plasma.
- 15 3. A method according to claim 1 or 2, wherein the fluorine-containing etchant comprises XeF_2 , F_2 , ClF_3 or mixtures thereof.
 - 4. A method according to claim 1 or 2, wherein the fluorine-containing etchant is XeF₂.
- 20 5. A method according to any preceding claim, further comprising the step of removing the mask and remaining protecting substance.
 - 6. A method according to any preceding claim, wherein the protecting substance is a fluorocarbon polymer of the general formula $C_{\gamma}F_{\chi}$.
 - 7. A method according to claim 6, wherein the protecting substance is of the general formula $n(CF_2)$.
 - 8. A method according to any one of claims 1 to 5, wherein

the protecting substance is of the form C_vH_x .

6 4 CM

- 9. A method according to claim 8, wherein the protecting substance is of the general formula $n(CH_2)$.
- 10. A micromechanical device formed by the method of any preceding claim.
 - 11. A micromechanical device according to claim 10, comprising a series of adjacent fingers separated by trenches.
- 12. A micromechanical device according to claim 11, wherein10 the trenches are in communication.
 - 13. An apparatus for manufacturing a micromechanical device comprising:
 - (a) means for etching a substrate, having a mask thereon, to a desired depth;
- (b) means for depositing a layer of a protecting substance on the exposed surfaces of the substrate and mask;
 - (c) means for selectively removing the protecting substance; and
- (d) means for providing a fluorine-containing etchant for etching the unprotected areas.
 - 14. An apparatus according to claim 13, further comprising means for removing the mask and the remaining protecting substance.




Fig. 1




Fig. 2

Same A.




Fig. 3








Fig. 4

PCT/GB99/00774









SUBSTITUTE SHEET (RULE 26)

.. INTERNATIONAL SEARCH REPORT

Internati Application No
PCT/GR 99/00774

		PC	T/GB 99/00774	
A. CLASSIF IPC 6	FICATION OF SUBJECT MATTER H01L21/3065			
According to	International Patent Classification (IPC) or to both national classificat	tion and IPC		
	SEARCHED			
Minimum do IPC 6	cumentation searched (classification system followed by classificatio HO1L B81C	n symbols)		
Documentat	ion searched other than minimum documentation to the extent that su	ch documents are included	in the fields searched	
Electronic de	ata base consulted during the International search (name of data bas	e and, where practical, seat	ch terms used)	
C. DOCUME	ENTS CONSIDERED TO BE RELEVANT			
Category °	Citation of document, with indication, where appropriate, of the rele	vant passages	Relevant to claim No.	
X	DE 42 41 045 C (BOSCH GMBH ROBERT 26 May 1994)	1,6,7, 10,13,14 2-4	
Y	see the whole document			
X	EP 0 729 175 A (IBM) 28 August 19	96	1,5,10, 11	
	see column 1, line 1 - column 4, figures 3,4	line 32;		
X	EP 0 822 584 A (SURFACE TECH SYS 4 February 1998 cited in the application see page 2, line 3 - page 4, line see page 8, line 21 - line 32; cl 1,5,8-10,18,19,21,22; figure 1	43	8,9,13, 14	
	_	/		
X Furt	her documents are listed in the continuation of box C.	X Patent family mem	ibers are listed in annex.	
"A" docume consider filling of "L" docume which citatio	ent defining the general state of the art which is not lered to be of particular relevance document but published on or after the international	or priority date and not cited to understand the invention "X" document of particular r cannot be considered involve an inventive standover of cannot be considered of document is combined	d after the international filing date in conflict with the application but a principle or theory underlying the elevance; the claimed invention novel or cannot be considered to ap when the document is taken alone elevance; the claimed invention to involve an inventive step when the with one or more other such docuon being obvious to a person skilled	
"P" docume	nterns and published prior to the international filing date but han the priority date claimed	in the art. "&" document member of the same patent family Date of mailing of the international search report		
	actual completion of the International search			
	June 1999	15/06/199	9 	
Name and	mailing address of the ISA European Patent Office, P.B. 5818 Patentiaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Micke, K		

1

INTERNATIONAL SEARCH REPORT

Internative Application No
PCT/GB 99/00774

Category ° Cita X	us 5 316 979 A (MACDONALD NOEL C ET AL) 31 May 1994 see the whole document IBBOTSON D E ET AL: "Plasmaless dry etching of silicon with fluorine-containing compounds" JOURNAL OF APPLIED PHYSICS, NOV. 1984, USA, vol. 56, no. 10, pages 2939-2942, XP002910845 ISSN 0021-8979 see abstract see page 2939, column 1, paragraph 1 - column 2, paragraph 2; table 2	1,10-12 2-4
Y	US 5 316 979 A (MACDONALD NOEL C ET AL) 31 May 1994 see the whole document IBBOTSON D E ET AL: "Plasmaless dry etching of silicon with fluorine-containing compounds" JOURNAL OF APPLIED PHYSICS, NOV. 1984, USA, vol. 56, no. 10, pages 2939-2942, XP002910845 ISSN 0021-8979 see abstract see page 2939, column 1, paragraph 1 -	1,10-12
Y	31 May 1994 see the whole document IBBOTSON D E ET AL: "Plasmaless dry etching of silicon with fluorine-containing compounds" JOURNAL OF APPLIED PHYSICS, NOV. 1984, USA, vol. 56, no. 10, pages 2939-2942, XP002910845 ISSN 0021-8979 see abstract see page 2939, column 1, paragraph 1 -	
	etching of silicon with fluorine-containing compounds" JOURNAL OF APPLIED PHYSICS, NOV. 1984, USA, vol. 56, no. 10, pages 2939-2942, XP002910845 ISSN 0021-8979 see abstract see page 2939, column 1, paragraph 1 -	2-4

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internati Application No
PCT/GB 99/00774

Patent document cited in search report	rt	Publication date	í	Patent family member(s)	Publication date
DE 4241045	С	26-05-1994	WO	9414187 A	23-06-1994
			EP	0625285 A	23-11-1994
			JP	7503815 T	20-04-1995
			US 	5501893 A	26-03-1996
EP 0729175	Α	28-08-1996	JP	8250466 A	27-09-1996
2. 2. 2. 2.			US	5658472 A	19-08-1997
EP 0822584	Α	04-02-1998	JP	10144654 A	29-05-1998
US 5316979	Α	31-05-1994	US	5198390 A	30-03-1993